

PRODUCT	7056AL
Maximum Temp (°F)	450
Density (gm/cc)	1.5
Viscosity (cps)	40,000
Hardness (Shore D)	65
Tensile Strength (psi)	10,000
Thermal Conductivity BTU-in/hr. °F Ft. ²	20
Thermal Expansion (10 ⁻⁶ /°C)	3.4
Dielectric Strength (volts/mil)	100
Volume Resistivity (ohm-cm)	10 ⁸
Elongation %	3.0
Thermal Stability % (1000 hr. @ 200 °C)	0.3
Shrinkage (% max.)	0.3
Moisture Absorption % (30 days @ 50 °C)	0.5
Components Color	2-Silver
Mix Ratio (R/H)	N/A
Cure at R.T.	4-8 min.
Cure at 250°F	

Stucco per Alluminio istantaneo : basta premere la siringa , mischiare con l'apposita paletta e applicare . Indurisce in 4- 8 minuti senza colare .

